FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
★ ★ ★ ★ ★
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2014-15/ **Date: 19-02-2015**

1. TESTING OF FINE AGGREGATES :

Sub: Testing of Fine Aggregates.
{Project*:Construction of Class rooms at Doddabommasandra in Ward No.10 (Doddabommasandra)of Vidyaranyapura Sub-Division}

Ref.: Letter No. Testing/BUB/2014-15, dated 16-02-2015

Sample supplied to lab by: Sri.A.Krishnareddy, Contractor, Bangalore.

Report required for: Assistant Executive Engineer, Vidyaranyapura Sub-Division. BBMP, Bangalore.

TABLE - 1.1 : SIEVE ANALYSIS :

IS Sieve Size, mm	Percentage Passing	Specification as Per IS: 383-1970(Reaffirmed 2007) Percentage Passing			Remarks
		Zone-I	Zone-II	Zone -III	
04.75	97.50	90-100	90-100	90-100	The Sample Conforms to Grading **Zone-II**
02.36	83.00	60-95	75-100	85-100	
01.18	73.10	30-70	55-90	75-100	
600. mic	47.00	15-34	35-59	60-79	
300.mic	19.30	5-20	8-30	12-40	
150.mic	2.90	0-10	0-10	0-10	

TABLE 1.2 ;

Sl No	Test Conducted	Sample	Results	Requirements as Per IS. Specification IS :383-1970 (Reaffirmed 2007)
1	Silt Content	001	1.44%	Not more than 8%
2.	Specific Gravity	----	2.56	-------

* As furnished by Client.
The Results relate only to the items tested.

AE-VD
SRO

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore - 97

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Compus
BANGALORE UNIVERSITY
Bangalore-560 056.

19/2/15

Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail. manjeshl@yahoo.com

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2014-15/ **Date: 19-02-2015**

1. TESTING OF COARSE AGGREGATES (40 mm):

Sub: Testing of Coarse Aggregates.
{Project*:Construction of Class rooms at Doddabommasandra in Ward No.10 (Doddabommasandra)of Vidyaranyapura Sub-Division}

Ref.: Letter No. Testing/BUB/2014-15, dated 16-02-2015

Sample supplied to lab by: Sri.A.Krishnareddy, Contractor, Bangalore.

Report required for: Assistant Executive Engineer, Vidyaranyapura Sub-Division. BBMP, Bangalore.

Table - 1.1 : SIEVE ANALYSIS :

IS Sieve Size, mm	Percentage passing	Requirements as per IS 383-1970 (Reaffirmed on 2007) % Passing	
	40 mm Sample	*Single size*	*Graded*
40mm	98.00	85-100	95 – 100
20mm	64.00	0 -20	30- 70
10mm	21.30	0 -5	10- 35
4.75mm	Nil	------	0 - 5

TABLE 12 :

SL No	Test conducted	Sample No	Results	Requirements as per IS:383-1970 & Test Conforms to IS 2386(Part I to IV) – 1963 (Reaffirmed on 2007)
1.	Flakiness Index	As above	16.20 %	Not to exceed 25 %
2.	Crushing value	----,,----	25.70 %	Not to exceed 45 % for concrete other than for wearing surfaces and 30% for concrete for wearing surfaces

* As furnished by Client.
The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Campus
BANGALORE UNIVERSITY
Bangalore-560 056.

Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail. manjeshl@yahoo.com

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2014-15/

Date: 25-02-2015

1. TEST REPORT ON CEMENT:

Sub: Testing of 53 Grade Cement Sample (IS 12269-1987).
{Project*:Construction of Class rooms at Doddabommasandra in Ward No.10 (Doddabommasandra)of Vidyaranyapura Sub-Division}
Ref.: Letter No. Testing/BUB/2014-15, dated 16-02-2015
Sample supplied to lab by: Sri.A.Krishnareddy, Contractor, Bangalore.
Report required for: Assistant Executive Engineer, Vidyaranyapura Sub-Division. BBMP, Bangalore.

PHYSICAL TESTS ON CEMENT

Brand* : Birla
Grade * : 53
Type * : OPC
Date : 17-02-2015 to 24-02-2015

SL No	Name of Test	Results	Requirements as per
		Cement Sample	IS 12269-1987
1	Initial setting time	**160min**	Shall not be less than 30 min
2	Final setting time	**250min**	Shall not be more than 600 min
3	Fineness (by dry sieving on IS 90 micron sieve)	**2.40 %**	Not to exceed 10.0%
4	Soundness test(by Le-Chatelier's method)	**1.50 mm**	Shall not be more than 10 mm
5	Compressive strength c) 3 days (average of three results) d) 7 days (average of three results)	**29.00 N/ Sq mm** **41.50 N/Sq mm**	Shall not be less than 27 N/Sqmm Shall not be less than 37N/Sqmm

* As furnished by Client.
The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Compus
BANGALORE UNIVERSITY
Bangalore-560 056.

29/2/2015
Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail. manjeshl@yahoo.com

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
★ ★ ★ ★ ★
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2014-15 **Date: 19-02-2015**

1. TEST REPORT ON REINFORCEMENT STEEL :

Sub: Testing of Reinforcement Steel of diameter 10mm.
{Project*:Construction of Class rooms at Doddabommasandra in Ward No.10 (Doddabommasandra)of Vidyaranyapura Sub-Division}
Ref.: Letter No. Testing/BUB/2014-15, dated 16-02-2015
Sample supplied to lab by: Sri.A.Krishnareddy, Contractor, Bangalore.
Report required for: Assistant Executive Engineer, Vidyaranyapura Sub-Division. BBMP, Bangalore.

TABLE – 1

SL No	Details	For 10mm	
		Test Results	Min Req as per IS 1786-2008
01	Observed diameter of bar	**10.0mm**	10.0mm
02	Observed Wt/m Length **Kg/m**	**0.621**	0.567
03	Proof stress/Yield stress, fy , **N/mm^2**	**560.0**	500.0
04	Bend/ Re bend Test	**Ok**	---
05	Percentage of Elongation, %	**20.40**	12.00
06	Ultimate Tensile Strength **N/mm^2**	**626.0**	545.0

*As furnished by Client.
The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Campus
BANGALORE UNIVERSITY
Bangalore-560 056.

19/2/2015
Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail. manjeshl@yahoo.com

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
Accredited by NAAC

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

JNANA BHARATHI
BANGALORE - 560 056

BUB/CTE/2014-15

DATE: 09-04-2015

1. TEST REPORT ON CEMENT CONCRETE CUBES:

Sub: Testing of Concrete Cubes (28 days Compressive Strength)
{Project*:Construction of Class rooms at Doddabommasandra in Ward No.10 (Doddabommasandra)of Vidyaranyapura Sub-Division}
Ref.: Letter No. Testing/BUB/2014-15, dated 07-04-2015
Sample supplied to lab by: Sri.A.Krishnareddy, Contractor, Bangalore.
Report required for: Assistant Executive Engineer, Vidyaranyapura Sub-Division. BBMP, Bangalore.

RESULTS OF COMPRESSIVE STRENGTH ON CEMENT CONCRETE CUBE SPECIMENS

Dimensions of Specimen : 150 X 150 X 150mm

Grade of Concrete* : M_{20}

TABLE 1.1 :

Sl No	Location/ Identification *	Date of Casting*	Date of Testing	Age in Days	C/S Area in Mm^2	Maximum Load in K.N	Compressive Strength (N/mm^2)	Avg. Value
1	001	10-03-15	07-04-15	28	22500	530	23.55	**23.32**
	002	"	"	"	"	520	22.88	
	003	"	"	"	"	530	23.55	

* As furnished by Client.
The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Compus
BANGALORE UNIVERSITY
Bangalore-560 056.

9/4/15

Dr. MANJESH .L
ME (Civil Engg) Ph D MISTE.MIRC
Associate Professor
Department of Civil Engineering
Bangalore University Jnanabharathi Campus
BANGALORE- 560 056
e- mail. manjeshl@yahoo.com

Phone Off: 080-22961935 / 1946
E-mail: centrans9@gmail.com

BANGALORE UNIVERSITY
DEPARTMENT OF CIVIL ENGINEERING

JNANA BHARATHI
BANGALORE - 560 056

FOR QUALITY & EXCELLENCE IN HIGHER EDUCATION
Accredited by NAAC

BUB/CTE/2014-15/ Date: 19-02-2015

1. TEST REPORT ON BRICKS:

Sub: Test Report on Bricks.
{Project*: Construction of Class Rooms at Doddabommasandra in Ward No.10 (Doddabommasandra) of Vidyaranyapura Sub-Division}
Ref.: Letter No. Testing/BUB/2014-15, dated 16-02-2015
Sample supplied to lab by: Sri.A.Krishnareddy, Contractor, Bangalore.
Report required for: Assistant Executive Engineer, Vidyaranyapura Sub-Division, BBMP, Bangalore.

TABLE I. WATER ABSORPTION TEST:

Sl No	Brand Name	Water absorption %	Average value %	Normal Values
1	001	8.90	**8.84**	As per IS:1077-1992 water absorption shall not be more than 20.00%
2	002	8.70		
3	003	8.80		
4	004	8.80		
5	005	9.00		

II. COMPRESSIVE STRENGTH :

Sl No	Brand Name	Compressive Strength N/Sq.mm	Average value N/Sq.mm	Normal Values
1	001	6.10	**5.94**	---------
2	002	5.90		
3	003	6.00		
4	004	5.90		
5	005	5.80		

I1I. EFFLORSCENCE:

Sl No	Brand	Efflorescence	Explanation as per IS: 3495:1992(Part-II)
1	001	Nil	Not more than 10 % of the exposed area of the brick is covered with a thin deposit of salts.
2	002	Nil	
3	003	Nil	
4	004	Nil	
5	005	Nil	

*As Furnished by Client.
The Results relate only to the items tested.

G.R. HARISH
Professor
Department of Civil Engineering
Jnana Bharathi Compus
BANGALORE UNIVERSITY
Bangalore-560 056.

19/02/2015
Dr. MANJESH J.
ME(Civil Engg.) Ph.D. MISTE, MIRC
Associate Professor
Department of Civil Engineering
Bangalore University, Jnanabharathi Campus,
BANGALORE 560 056.
E-mail: manjesh@yahoo.com